

Wan Hashim Wan Ibrahim Siti Noor Linda Taib Norsuzailina Mohamed Sutan

CIVIL ENGINEERING, SCIENCE AND TECHNOLOGY CHALLENGES: STRUCTURAL ENGINEERING AND CONSTRUCTION MATERIALS

© Wan Hashim Wan Ibrahim, Siti Noor Linda Taib, Norsuzailina Mohamed Sutan

2022

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording or otherwise, without the prior permission of the publisher.

Published in Malaysia by UNIMAS Publisher, Universiti Malaysia Sarawak, 94300 Kota Samarahan, Sarawak, Malaysia.

Perpustakaan Negara Malaysia

Cataloguing-in-Publication Data

CIVIL ENGINEERING, SCIENCE AND TECHNOLOGY CHALLENGES: STRUCTURAL ENGINEERING AND CONSTRUCTION MATERIALS / EDITED BY Wan Hashim

Wan Ibrahim, Siti Noor Linda Taib, Norsuzailina Mohamed Sutan.

Mode of access: Internet eISBN 978-967-2298-90-8

- 1. Structural engineering.
- 2. Building materials.
- 3. Government publications--Malaysia.
- 4. Electronic books.
- I. Wan Hashim Wan Ibrahim. II. Siti Noor Linda Taib.
- III. Norsuzailina Mohamed Sutan.

624.1

The book is based on scientific and technological advances in various Structural Engineering and Construction Materials areas of Civil Engineering. It nurtures therefore the exchange of discoveries among research workforces worldwide including those focusing on the vast variety of facets of the fundamentals and applications within the Structural Engineering and Construction Materials arena. To offer novel and rapid developments, this book contains original contributions covering theoretical, physical experimental, and/or field works that incite and promote new understandings while elevating advancement in the Structural Engineering and Construction Materials fields. Works in closing the gap between the theories and applications, which are beneficial to both academicians and practicing engineers, are mainly of interest to this book that paves the intellectual route to navigate new areas and frontiers of scholarly studies in Structural Engineering and Construction Materials.

CIVIL ENGINEERING, SCIENCE AND TECHNOLOGY CHALLENGES: STRUCTURAL ENGINEERING AND CONSTRUCTION MATERIALS

Editors in Chief

Wan Hashim Wan Ibrahim Siti Noor Linda Taib Norsuzailina Mohamed Sutan

Editors

Raudhah Ahmadi Idawati Ismail

Abdul Razak Abdul Karim

Azida Rashidi

Delsye Teo Ching Lee

Mohd Raduan Kabit

Mohammad Ibrahim Safawi bin Mohammad Zain

Ahmad Kueh Beng Hong

Mohammad Abdul Mannan

Ng Chee Khoon

Leonard Lim Lik Pueh

Alsidqi Hasan

Charles Bong Hin Joo

Mah Yau Seng

Norazzlina bt M. Sa'don

Advisory Editors

Taksiah A.Majid

Megat Azmi Megat Johari

Zainah Ibrahim

Mohd Saleh Jaafar

Farah Nora Aznieta Abd. Aziz

Fadzli Mohamed Nazri

Ahmad Baharuddin Abd. Rahman

Md. Habibur Rahman Sobuz

Copy Editors/Proofreaders

Chuah Kee Man Zayn Al-Abideen Gregory Helmy Hazmi Annisa Jamali

Layout Editor

Nur 'Ain Binti Shardi Freddy Yeo Kuok San Rose Sima Anak Ikau

TABLE OF CONTENTS

HAP	IER IIILE OF CHAPIERS	PAGE NO
1	Modified Cement System: Durability And Aesthetics	1
2	Utilization Of Recycled Aggregate As Coarse Aggregate In Concrete	6
3	Effect Of Aggregates And Curing Conditions On The Compressive Strength Of Concr With Age	rete 13
4	Effect Of Seawater On The Properties Of Epoxy Modified Concrete	21
5	Study The Structural Behavior Of Ferrocement Beam	29
6	Effect Of PFA On Strength And Water Absorption Of Mortar	37
7	Laboratory Study Of Water Absorption Of Modified Mortar	42
8	Performance Of Profiled Steel Sheet Dry Board System Under Flexural Bending A Vibration	And 48
9	The Effect Of Reinforcement, Expanded Polystyrene (EPS) And Fly Ash On The Stren Of Foam Concrete	gth 57
10	Status Of Industrialized Building System Manufacturing Plant In Malaysia	65
11	Evaluation Of Acacia Mangium In Structural Size At Green Condition	76
12	Basic And Grade Stress For Some Timber In Sarawak	84
13	The Behavior Of Strength Properties From Three Different Tree Boles Of Aras Sarawak	In 88
14	Initial Surface Absorption Of Pozzolan And Polymer Modified Mortar	93
15	The Influence Of Finely Ground Mineral Admixture (FGMA) Of Efflorescence	99
16	Characterization Of Early Pozzolanic Reaction Of Calcium Hydroxide And Calci Silicate Hydrate For Nanosilica Modified Cement Paste	^{um} 106
17	Strength Characteristics Of Mortar Containing Different Sizes Glass Powder	113
18	Influence Of Silica Based Waste Materials On The Mechanical And Physical Proper Of Mortar	ties 120
19	Effect Of Curing And Mixing Methods On The Compressive Strength Of Mor Containing Oil	^{tar} 126
20	Improving The Strength Performance Of High Volume Periwinkle Shell Ash Blend Cement Concrete With Sodium Nitrate As Accelerator	^{ded} 133
21	Chloride Resistance Of Blended Ash Geopolymer Concrete	138
22	Evaluation Of Water Hyacinth Stem Ash As Pozzolanic Material For Use In Blend Cement	^{ded} 150
23	Pozzolanic Properties Of Glass Powder In Cement Paste	158
24	Effect Of Organic Soil On Strength Properties Of Compressed Cement-Soil Block	166
25	Effect Of Base Isolator On The Structural Response Of Reinforced Concrete Multistor Building Under Seismic Loads	

TABLE OF CONTENTS cont.

CHAPT	TER TITLE OF CHAPTERS	PAGE NO
26	Toner Used In The Development Of Foamed Concrete For Structural Use	184
27	Finite Element Simulation Of Damage In RC Beams	192
28	Seismic Performance Of Damper Installed In High-Rise Steel Building In Bangladesl	n 200
29	Characteristics Of Steel Fiber Reinforced Concrete With Recycled Coarse Aggregate	213
30	Finite Element Analysis Of A Strengthened Beam Deliberating Elastically Isotropic A Orthotropic CFRP Material	And 218
31	Compressive Strength Of Foamed Concrete In Relation To Porosity Using SEM Image	ges 229
32	Predicting The Structural Performance Of Sandwich Concrete Panels Subjected To B Load Considering Dynamic Increase Factor	last 241
33	Partial Replacement Of Cement By Coffee Husk Ash For C-25Concrete Production	258
34	Porosity, Permeability And Microstructure Of Foamed Concrete Through SEM Ima	ges 267
35	Some Mechanical Characteristics Of Concrete Reinforced With Dried Water Hyaci And Quarry Dust As Fine Aggregates	nth 282
36	Potential Use Of Cinder Gravel As An Alternative Base Course Material Throughending With Crushed Stone Aggregate And Cement Treatment	184 192 200 213 And 218 ages 229 Blast 241 258 267 inth 282 bugh 290 ortar 302 315 aded 324 For 331 Mix 349 ssive 367 med 379
37	Water Permeability And Chloride And Sulphate Resistance Of Rubberised Fibre Mon	rtar 302
38	Case Study Of Structural Health Monitoring In India And Its Benefits	
39	Comparing Compressive Strengths Of Layered And Random Placement Of Expan Polystyrene Wastes In Quarry Dust Blocks	ded 324
40	Experimental Study On Application Of Marble Waste As Conventional Aggregate Base Course Materials	For 331
41	Evaluation Of The Performance Of Waste Marble Dust As A Mineral Filler In Hot- Asphalt Concrete	Mix 349
42	Linear And Nonlinear Free Vibration Analysis Of Rectangular Plate Compres Strength Of Mortar Containing Oil	sive 367
43	Influence Of Oil Palm Spikelets Fibre On Mechanical Properties Of Lightweight Foar Concrete	^{ned} 379
44	Experimental Study On Behavior Of Unprotected Foamed Concrete Filled Steel Hol Column Under Fire	low 388

CHAPTER 13

THE BEHAVIOR OF STRENGTH PROPERTIES FROM THREE DIFFERENT TREE BOLES OF ARAS IN SARAWAK

Gaddafi Ismaili^{1*}. Badorul Hisham Abu Bakar² and Khairul Khuzaimah Abdul Rahim³

ABSTRACT

Aras had been selected and tested in small clear specimens. Sampling of test specimens are made from three sections of the tree bole namely from bottom, middle, and top parts. This paper looks into the information of strength properties from three sections of sampled. The strength properties test required are the modulus of rupture, modulus of elasticity and compression stress parallel to grain. Meanwhile, the physical properties' test referred to moisture content and basic density. The testing conducted in two different conditions of the trees, which were referred to green and air-dry condition. It was found that the average mean values for modulus of rupture, modulus of elasticity and compressive stress parallel to grain tested at green condition were 47.52N/mm², 6358.56N/mm² and 22.42N/mm² respectively meanwhile at air- dry condition were 70.49N/mm², 8217.64N/mm² and 34.07N/mm² respectively. Meanwhile, the average mean values for moisture content at green condition were 83.34% whilst at the air-dry condition were 12.33%. Basic density remains unchanged from both conditions.

Keywords: Modulus of rupture, modulus of elasticity, compression stress parallel to grain, moisture content, basic density

INTRODUCTION

Generally, log production in Malaysia is mainly to accommodate the huge demand for general utility timber for industrial purposes. Nowadays, timber industries in Malaysia have involved into cores of plywood and make up the major constituent of fibreboard, particleboard, interior construction wood, and other low grade use. [1]. Sarawak consists of numerous indigenous species of fast growing timber. From these species, there are several which has been identified to be potential species for light wood industries utilisation and for engineering structural design purposes as alternative species. The potential species are referred to Engkabang jantong, Aras, Terbulan, Kelampayan, Sawih, Benuang and, etc. Each of these species has its own characteristics and behaviour whether in terms of physical or strength properties. Therefore, there is a need to get some basic information on its strength and physical properties. Small clear specimens or defect free samples were used to know the strength properties and physical properties distribution within the tree bole viz., from bottom, middle and top parts. For this paper, Aras has been selected for this study.

^{1*} Faculty of Engineering, Universiti Malaysia Sarawak Email:igaddafi@unimas.my

² School of Civil Engineering, Universiti Sains Malaysia

³ Applied Forest Science and Industry Development Division, Sarawak Forestry Corporation Sdn. Bhd., Malaysia

Aras is a type of tree known by the locals in Sarawak. It is known by its botanical name as *Ilex cissoidea*. In Sabah, this species is known as *bangkulatan* and *morogis*, while in Peninsular Malaysia, this species is known as *timah-timah*. Meanwhile, in Indonesia it is known as Mensira gunung. *Ilex cissoidea* is categorized in Aquifoliaceae family that is commonly found throughout the temperate and tropical regions of the world, mainly in South East Asia. Its sapwood is not differentiated from the heartwood, which is white and darkens on exposure to be yellow-brown. The timber is of medium density Light Hardwood, ranging from 560-595kg/m³ in air-dry condition. The timber is non-durable and is subject to attacks by sapstain fungi. The grain is straight, and the texture is fine but uneven due to the presence of the broad rays. The split surface has a considerable sheen. This timber is reported to season well with only slight splitting [2]. This genus is rather rare in an occurrence and coupled with its small size. The timber is very unlikely to be of any commercial importance. However, this timber has been tried successfully for match splints and may be a good furniture timber if available in large enough quantities.[2]

MATERIALS AND TESTING METHODS

MATERIALS AND SAMPLING METHODS

A total of 335 selected specimens of Aras were used in this study. The collection of the species was done at Sabal Reforestation Plot. The selected species were then be made into three sections of tree bole namely bottom, middle and top. At the site, the log of about 1.53m in length was then ripped through the pith to obtain two flitches and transported to the processing factory where the flitches be machined into boards. The boards were subsequently machined to produce exactly 20mm square sticks. The sticks were visually graded, and only defect free green as well as air-dry samples were cut into specified length and brought to mechanical testing facility to be tested.

STRENGTH PROPERTIES

All the strength properties were conducted in accordance to the British Standard BS 373: 1957 [3]. The results were obtained from the testing conducted by using destructive test (DT) in two different timber conditions, i.e. green and air-dry conditions. The strength properties that were tested were the modulus of rupture, modulus of elasticity and compression stress parallel to grain. An Instron Universal Testing Machines with loading capacity of 50kN was used to determine the strength values of the wood specimens. The loading rate for static bending and compression parallel to grain was 6.6 mm per minimum and 0.6 mm per minimum respectively. The testing room was maintained at temperature of 20±3°C.

PHYSICAL PROPERTIES

MOISTURE CONTENT DETERMINATION

Moisture content (MC) determination was conducted directly after the wood processing was completed. At that point, the initial weights were taken. Then, samples were placed in the oven at 103±2°C until the constant weight was achieved. The percentage of moisture content was calculated on the dry weight basis. The formula for calculating moisture content is shown below

$$MC (\%) = \frac{\text{Initial weight - Oven dried weight}}{\text{Oven dried weight}} \times 100$$
 (1)

BASIC DENSITY DETERMINATION

The specimens were calculated from the ratio of oven-dried weight to green volume. Water displacement method was used to get the green volume, and the dry weight was measured using an electronic balance. The formula for calculating the basic density is as shown below.

Basic density
$$(g/cm^3) = \frac{\text{Oven dried weight}}{\text{Green volume}}$$
 (2)

RESULTS AND DISCUSSION

The test results for modulus of rupture, modulus of elasticity, compressive stress parallel to grain, basic density and moisture content of small clear specimens of Aras are shown in Table 1. Total number of 67 specimens from green and air- dry condition was tested for each test. The basic density was $0.37g/cm^3$ and classified under Light Hardwood based on Malaysian Grading Rules [4]. In terms of compressive strength with reference to Malaysian Grading Rule, it is classified under the strength group SG7 [4]. The average mean values for modulus of rupture, modulus of elasticity and compressive stress parallel to grain tested at green condition were 59.01N/mm², 7288.10N/mm² and 28.25N/mm² respectively. This timber can be use for joinery, matches, pattern making, boxes and crates, furniture components, plywood, light construction, carvings and wooden shoes. [5].

Table 1: Test results of small clear specimens of Aras.

Statistical Analyses	Modulus of rupture (N/mm²)	Modulus of elasticity (N/mm²)	Compression stress parallel to grain (N/mm ²)	Density (g/cm³)	Moisture content (%)
Mean	57.40	7162.36	27.49	0.37	52.59
STDEV	15.75	1509.47	7.50	0.04	36.13
CV (%)	27.43	21.08	27.27	10.79	68.70
N	67.0	67.0	67.0	67.0	67.0

Note:

Mean= Mean values STDEV= Standard deviation CV= Coefficient of variation N= Number of specimens

DISTRIBUTION PATTERN OF STRENGTH PROPERTIES WITHIN THE TREE BOLE

The results for strength properties test for modulus of rupture, modulus of elasticity and compressive stress parallel to grain were represented in Figure 1, Figure 2 and Figure 3 respectively. From the observation, specimens at green condition showed the highest modulus of rupture mean values possessed by top tree bole with 49.29N/mm² followed by bottom and middle tree bole with the mean value of 46.79N/mm² and 46.48N/mm² respectively. For modulus of elasticity, the top tree bole remained with the highest mean value of 6604.07N/mm² followed by bottom and middle tree bole with mean values of 6301.71N/mm² and 6169.89N/mm² respectively. Meanwhile, the mean value for compression stress parallel to grain revealed that bottom and top tree bole recorded with the same mean value of 22.70N/mm² whilst the middle treetop with 3.5% different with mean value of 21.87N/mm².

Meanwhile, at the air-dry condition, the middle tree bole section recorded the highest modulus of rupture mean value with 73.76N/mm² followed by the bottom and top tree bole with mean values of 69.68N/mm² and 68.04N/mm² respectively. The middle tree bole section also registered the highest mean value for modulus of elasticity and subsequently followed by top and bottom tree bole section with the mean values of 8618.11N/mm², 8159.91N/mm² and 7874.89N/mm² respectively. Moreover, for compression stress parallel to grain, middle tree bole section with the mean value of 36.12N/mm² also gave the highest mean value followed by bottom and top tree section with mean values of 30.91N/mm² and 35.20N/mm² respectively.

The differences between the three tree bole sections at the green and air-dry condition are represented in its percentages different. For modulus of rupture, the middle tree bole section at the air-dry is 37% higher compared to at green condition, which was the highest followed by bottom and top section with 32.8% and 27.6% respectively. The same case was observed for modulus of elasticity, where the middle section has the highest difference followed by bottom and top with the condition showed the difference of 28.4%, 20.0% and 19.1% higher compared to than at green condition respectively. The compression stress parallel to grain also showed that middle tree bole section has the highest difference with air-dry giving higher values than green condition at 39.5% followed by top and bottom section at 35.5% and 26.6% respectively. From the finding, the strength properties values for Aras at green condition was found to be higher at the top tree bole section and with a 3.2% difference compared to the strength properties values at the bottom tree bole section. At the air-dry condition, the higher strength properties values possessed by the middle tree bole section with 5.2% different as compared to the strength properties values at the bottom tree bole section. It was found that, the outcome from this finding was contrary with [6], where timbers from butt logs are expected to be slightly stronger than top logs. However, the basic density results for both green and air-dry condition was agreed with [6], where timbers at the bottom tree bole section are slightly denser than the top tree bole section. Timber is physically specified as heterogeneous characteristic. This characteristic prompt to fluctuate in its strength properties even though within the same species. The difference in the strength properties between species is further accentuated if injurious defects such as knots, sloping grain are present, as some species are more prone to contain such defects [7].

DISTRIBUTION PATTERN OF PHYSICAL PROPERTIES WITHIN THE TREE BOLE

For the physical properties, the highest mean value of moisture content at green condition possessed by middle tree bole with the mean value of 86.95% followed by bottom and top tree bole with mean value of 84.08 and 78.98% respectively. At top tree bole section had the highest basic density with the value of 0.38g/cm³, meanwhile at the bottom and middle tree bole gave the same mean value of 0.36g/cm³.

At air-dry condition, the bottom tree bole section had the highest moisture content compared to top and middle tree bole section with value of 12.69%, 12.22% and 12.09% correspondingly. The highest basic density possessed by the top tree bole section with 0.38g/cm³ followed by middle and top tree bole with the value of 0.37g/cm³ and 0.36g/cm³ respectively. However, it was obvious that the difference of moisture content was higher at green compare to air-dry condition by middle section with the highest difference followed by bottom and top section by 86.1 %, 84.9 % and 84.5 % respectively. The results at air-dry condition were in agreement with [4], where wood increases in strength as it dries. The results for moisture content and basic density test are presented in Figure 4 and Figure 5 respectively.

CONCLUSION

Aras is classified under Light Hardwood and in terms of its strength, it is categorized under the strength group SG7. The species was recommended mainly for general utility for furniture making and other non-structural applications. It was found that the strength properties values for modulus of rupture, modulus of elasticity and compressive stress parallel to grain at green condition showed that highest values possessed by top tree bole section. Whilst at the air-dry condition, the highest value was possessed by middle tree bole section. The basic density also showed a similar trend which was reported higher at top tree bole section for both green and air-dry condition.

ACKNOWLEDGMENT

The authors would like to gratefully acknowledge everyone involve in this project, especially to Malaysia Comprehensive University Network (UNIMAS, UiTM and UMS) for the research funding GL/F02/MCUN/17/2020, Universiti Malaysia Sarawak, Research Manager, Dr. Alik Duju. Thank you all for your guidance and support.

REFERENCES

- [1] Krishnapillay B. and Abdul Razak Mohd Ali (1998). Feasibility of Planning High Quality Timber Species in Peninsular Malaysia. In Proceeding of the Seminar on High Value Timber Species for Plantation Establishment-Teak and Mahoganies, 1-2 December 1998, Tawau, Sabah. 91-101pp
- [2] Anon. (2006). MTC Wood Wizard. Malaysian Timber Council. [WWW⁵]http://woodwizard.my/asearch.asp[Accessed 28 September 2008]
- [3] British Standard (1957). Methods of Testing Small Clear Specimen of Timber. British Standard Institution. BS 373: 1957. 31pp.
- [4] Anon. (2011). Malaysian Grading Rules, Malaysian Timber Industry Board, (MTIB), (2011). [WWW¹³][Accessed 2 August 2008]
- [5] Richter, H.G. & Dallwitz, M.J., 2000. Commercial timber: descriptions, illustrations, identification, and information retrieval. [WWW¹⁶] http://delta- intkey.com/wood/index.htm>[Accessed 12 Jun 2008]
- [6] Keith R. Bootle (1985), Wood in Australia: Type, properties and uses. McGraw-Hill Book Co. Australia. 29, 60-61pp.
- [7] R.G. Pearson, N.H. Kloot and J.D. Boyd (1962). Timber Engineering Design Handbook, Jacaranda Press Pty Ltd. Australia, 19, 22-23pp.

The book is based on scientific and technological advances in various Structural Engineering and Construction Materials areas of Civil Engineering. It nurtures therefore the exchange of discoveries among research workforces worldwide including those focusing on the vast variety of facets of the fundamentals and applications within the Structural Engineering and Construction Materials arena. To offer novel and rapid developments, this book contains original contributions covering theoretical, physical experimental, and/or field works that incite and promote new understandings while elevating advancement in the Structural Engineering and Construction Materials fields. Works in closing the gap between the theories and applications, which are beneficial to both academicians and practicing engineers, are mainly of interest to this book that paves the intellectual route to navigate new areas and frontiers of scholarly studies in Structural Engineering and Construction Materials

