



Faculty of Resource Science and Technology

**Drying Characteristics Variation in Dry Pre-treated Seven and 10-Year-
Old of *Acacia mangium***

Elia Anak Ambrose

**Master of Science
2022**

Drying Characteristics Variation in Dry Pre-treated Seven and 10-Year-Old of
Acacia mangium

Elia Anak Ambrose

A thesis submitted

In fulfillment of the requirements for the degree of Master of Science

(Wood Technology)

Faculty of Resource Science and Technology

UNIVERSITI MALAYSIA SARAWAK

2022

DECLARATION

I declare that the work in this thesis was carried out in accordance with the regulations of Universiti Malaysia Sarawak. Except where due acknowledgements have been made, the work is that of the author alone. The thesis has not been accepted for any degree and is not concurrently submitted in candidature of any other degree.

.....

Signature

Name: Elia Anak Ambrose

Matric No.: 18020023

Faculty of Resource Science and Technology

Universiti Malaysia Sarawak

Date:

ACKNOWLEDGEMENT

I would like to take this opportunity to those who have contributed directly and indirectly to this thesis. First and foremost, to my supervisor, Prof Dr. Ismail Jusoh for the patient, guidance, encouragement and advice he gave throughout my Master Degree's study. I have been lucky to have a supervisor who cares and is passionate about my work and guided me through my experiments and writing. I would like to thank Sarawak Timber Association for funding my study together with a scholarship of Forestry Nichemen from Sarawak Timber Industry Development Cooperation (STIDC). I would like to thank Dr Alik Duju, Madam Syarina, Mr Wong, Mr Perry, Mr Bolton, Mr Ibrahim and Mr Nuggah from Sarawak Forestry Cooperation for technical support, guiding and helping me in operating the equipment in Timber Research and Technical Training Centre. I am very thankful to the Faculty of Resource Science and Technology, University Malaysia Sarawak, for their support and Ministry of Higher Education financial support under the Fundamental Research Grant Scheme (FRGS) F07/FRGS/1622/2017. I am also thankful to Grand Paragon Sdn Bhd, Bintulu for their technical support, which made this research possible.

Not to forget my beloved family members especially my parents for their prayer, motivation and support relentlessly throughout my study. To all my friends and cousins, Emily, Yvonne, Fifi, Farahin, Iskandar, Beatrice, Wizzila, Elizabeth, Lionel, Seha, Bellnear and Shirinne who always there for me and accompanied me to the kiln drying room at night and helping me managed my sample boards. A very dearest thanks to them! Praise Lord Almighty God for his protection, guidance and blessing throughout the days of completing this project and thesis writing. Finally, I'm dedicating this master thesis to my beloved late grandfather, Mr William Lunyen for his prayer from above. This is for you.

ABSTRACT

In Sarawak, *Acacia mangium* is the primary species used for commercial forest plantation to reduce timber dependency from the natural forest. The wood has adequate strength, quality and durability for appropriate utilization and end-use. However, the uneven distribution of moisture content and drying defects are the primary problems in converting *Acacia mangium* wood into high-value products. The major cause of those problems is the presence of wet pockets in the dried wood. The objectives of this study were to (1) determine the untreated moisture content and the physical properties of seven and 10-year-old of *A. mangium* wood, (2) determine the effect of pre-treatments on the drying time, occurrence of wet pocket and drying defects in dried *A. mangium* boards, and (3) develop new drying schedules for seven and 10-year-old *A. mangium* board. Trees of seven and 10-year-old *A. mangium* were obtained from a plantation. The felled trees were rough sawn to 50 mm and 400 cm thick and long, respectively. Defects-free quarter and rift-sawn sample boards were selected and subsequently cut to a standard size of 27 mm (thickness) $\times$ 150 mm (width) $\times$ 690 mm (length). Three pre-treatments experimented were incision, forced air drying and pressure. The average basic wood density of 10-year-old *Acacia mangium* was significantly higher than seven-year-old *A. mangium*. The untreated moisture content of the seven-year-old is greater than the 10-year-old *A. mangium*. Results showed that pressure pre-treatment was the best for both seven and 10-year-old *A. mangium*. All sample boards treated with pressure did not show severe drying defects such as checks, collapse, and honeycombing. Mild schedule was recommended for both seven and 10-year-old *A. mangium*. Although the recommended schedule is not the fastest in terms of drying rate, it can reduce the occurrence of wet pocket and minimize the incidence of drying defects in both ages. The newly developed drying schedule for seven-year-old *A. mangium* indicate that kiln drying begins

with an initial dry-bulb temperature of 45 °C, the wet-bulb depression 1.7 °C and the final dry bulb temperature of 70 °C. For 10-year-old *A. mangium* begin with an initial dry-bulb temperature of 48 °C, wet-bulb depression 4.0 °C and the final dry bulb temperature of 71 °C. Application of the new drying schedule on flat sawn sample boards succeed with no severe drying defects. The new drying schedule for 10-year-old *A. mangium* able to reduce the occurrence of wet pocket.

Keywords: *Acacia mangium*, pre-treatment, wet pocket, drying schedule, drying defects

Variasi Ciri Pengeringan Dalam Pra-rawatan Kayu Kering Tujuh dan 10 tahun Acacia mangium

ABSTRAK

Di Sarawak Acacia mangium merupakan spesies utama untuk perladangan hutan komersial seterusnya mengurangkan kebergantungan sumber kayu dari hutan asli. Kayunya mempunyai kekuatan, kualiti dan ketahanan semulajadi yang memuaskan dan sesuai untuk kegunaan dan penghasilan produk. Walau bagaimanapun ketidakseragaman taburan kandungan kelembapan dan kecacatan pengeringan adalah masalah utama dalam menggunakan kayu A. mangium untuk menghasilkan produk yang bernilai tinggi. Faktor utama yang menyebabkan masalah ini adalah kehadiran poket basah dalam papan yang telah dikeringkan. Objektif-objektif kajian ini adalah (1) menentukan purata kandungan kelembapan kayu serta sifat fizikal kayu A. mangium berumur tujuh and 10 tahun, (2) menentukan kesan pra-rawatan terhadap masa pengeringan papan, kejadian poket basah dan kecacatan pengeringan pada papan kering yang telah menjalani pra-rawatan, dan (3) menghasilkan jadual pengeringan baru untuk papan A. mangium berumur tujuh dan 10 tahun. Pokok-pokok A. mangium berumur tujuh dan 10 tahun diperolehi dari sebuah ladang hutan. Semua pokok yang ditebang dipotong masing- masingnya mempunyai ketebalan dan panjang kasar 50 mm dan 400 mm. Papan gergaji potongan suku (quarter-sawn) dan ricih (rift-sawn) yang bebas dari cacat dipilih untuk dijadikan sampel bersaiz 27 mm (tebal) x 150 mm (lebar) x 690 mm (panjang). Tiga pra-rawatan yang diuji ialah insisi, pengeringan paksa udara dan tekanan. Purata ketumpatan kayu asas bagi kayu A. mangium berumur 10 tahun lebih tinggi dari yang berumur tujuh tahun secara signifikan Purata kandungan kelembapan hijau bagi kayu A. mangium berumur tujuh tahun lebih tinggi dari yang berumur 10 tahun secara signifikan. Keputusan menunjukkan penggunaan tekanan sebagai

pra-rawatan adalah yang terbaik untuk tujuh dan 10 tahun A. mangium. Semua sampel papan yang diberi pra-rawatan tekanan tidak menunjukkan kecacatan pengeringan yang teruk. Jadual pengeringan sederhana disyorkan untuk tujuh dan 10 tahun A. mangium. Walaupun jadual yang disyorkan ini tidak dapat mengeringkan kayu dengan cepat, ia boleh mengurangkan pembentukan poket basah dan meminimakan kecacatan pengeringan untuk kedua-dua umur. Jadual pengeringan yang baru dihasilkan untuk kayu tujuh tahun menunjukkan pengeringan tanur dimulakan dengan permulaan suhu bebuli kering 45 °C, rendahan bebuli basah 1.7 °C dan suhu akhir bebuli kering 70 °C untuk A. mangium berumur tujuh tahun. Bagi A. mangium berumur 10 tahun suhu permulaan bebuli kering ialah 48 °C rendahan bebuli basah 4.0 °C dan suhu akhir bebuli kering 71 °C. Aplikasi jadual pengeringan terhadap papan potongan tangen (flat-sawn) tidak menghasilkan kecacatan pengeringan yang teruk. Jadual pengeringan yang baru bagi A. mangium berumur 10 tahun adalah berkesan untuk mengurangkan kehadiran poket basah

Kata kunci: *Acacia mangium, pra-rawatan, poket basah, jadual pengeringan, kecacatan pengeringan*

TABLE OF CONTENTS

	Page
DECLARATION	i
ACKNOWLEDGEMENT	ii
ABSTRACT	iii
<i>ABSTRAK</i>	v
TABLE OF CONTENTS	vii
LIST OF TABLES	xii
LIST OF FIGURES	xiii
LIST OF ABBREVIATIONS	xv
CHAPTER 1: INTRODUCTION	1
1.1 Study Background	1
1.2 Problem Statement	5
1.3 Objectives	6
1.4 Chapter Summary	6
CHAPTER 2: LITERATURE REVIEW	8
2.1 Background of <i>Acacia mangium</i>	8
2.2 Properties of <i>Acacia mangium</i> Timber	9
2.3 Uses of <i>Acacia mangium</i>	10
2.4 Moisture in Wood	10

2.5	Wet Pocket in Wood	12
2.6	Wood Drying	15
2.7	Drying Schedule	17
2.8	Factor Affecting Wood Drying	19
2.9	Factor Influence Drying Rate	20
2.10	Wood Drying Defects	21
2.11	Chapter Summary	22
	CHAPTER 3: MATERIALS AND METHODS	24
3.1	Field Sampling	24
3.2	Tree Bucking	24
3.3	Log Sawing	25
3.4	Determination of Wood Physical Properties	25
3.4.1	Wood Density	25
3.4.2	Wood Shrinkage	26
3.5	Pre-treatment Study	27
3.5.1	Sample Boards Preparation and Determination of Initial Moisture Content	27
3.5.2	Incision Pre-treatment	28
3.5.3	Forced Air Dry Pre-treatment	29
3.5.4	Pressure Pre-treatment	29
3.5.5	Experimental Drying Chamber	30
3.5.6	Determination of Final Moisture Content (MC_f) and Area of Wet pocket	32

3.6	Quick Drying Test (QDT)	33
3.7	Determination of Drying Defect	34
3.7.1	Determination of degree of Surface and End Checks	34
3.7.2	Determine Degree of Deformation	35
3.7.3	Determination of Honeycombing	36
3.7.4	Determination of Collapse	36
3.8	Determination of Wet Pocket	37
3.9	Determination of Drying Time and Drying Rate	38
3.10	Developing New Drying Schedule	38
3.10.1	Drying Schedule Test (DST) for 27 mm of Seven-Year-Old <i>Acacia mangium</i>	40
3.10.2	Drying Schedule Test (DST) for 27 mm 10-Year-Old <i>Acacia mangium</i>	41
3.11	Statistical Analysis	42
3.12	Chapter Summary	42
	CHAPTER 4: RESULTS	45
4.1	Physical Properties of Seven and 10-Year-Old <i>Acacia mangium</i>	45
4.2	The effects of Pre-treatments on Drying Time and Drying Rate of <i>Acacia mangium</i>	46
4.2.1	Drying Time of Seven-Year-Old of <i>Acacia mangium</i>	46
4.2.2	Drying Rate of Seven-Year-Old <i>Acacia mangium</i>	48
4.3	The Effects of Pre-treatments on Drying Time and Drying Rate of 10-Year-Old <i>Acacia mangium</i>	49

4.3.1	Drying Time for 10-Year-Old <i>Acacia mangium</i>	49
4.3.2	Drying Rate of 10-Year-Old <i>Acacia mangium</i>	50
4.4	The Presence of Wet Pocket	51
4.4.1	The Effects of Pre-treatments in Alleviating Wet Pocket in Seven-Year-old <i>Acacia mangium</i>	52
4.4.2	The Effect of Pre-treatments in Alleviating Wet Pocket in 10-Year-Old <i>Acacia mangium</i>	53
4.5	Drying Defect Prior to Pre-treatments	55
4.6	Quick Drying Test (QDT) of <i>Acacia mangium</i>	59
4.7	Drying Schedule Test (DST)	60
4.7.1	Drying Schedule Test (DST) of Seven-Year-Old <i>Acacia mangium</i>	60
4.7.2	Drying Schedule Test (DST) for 10-Year-Old <i>Acacia mangium</i>	64
4.8	Recommended Drying Schedule for 27 mm Thickness of Seven and 10-Year-old <i>Acacia mangium</i>	67
4.9	Chapter Summary	68
	CHAPTER 5: DISCUSSIONS	70
5.1	Physical Properties of <i>Acacia mangium</i>	70
5.2	Effects of Pre-treatments on Rate of Drying	72
5.3	Wet Pocket in Dried <i>Acacia mangium</i>	74
5.4	The Effect of Pre-treatments on Development of Wet Pocket in Seven and 10-Year-Old <i>Acacia mangium</i>	75

5.5	Drying Defects of Pre-treated Boards	76
5.6	Recommended Drying Schedule for 27 mm Thick Boards for Seven and 10-Year-Old <i>Acacia mangium</i>	77
5.7	Summary of Discussion	79
	CHAPTER 6: CONCLUSIONS AND RECOMMENDATIONS	81
6.1	Conclusions	81
6.2	Recommendations	82
	REFERENCES	84
	APPENDICES	96

LIST OF TABLES

	Page
Table 3.1: Frequency of drying duration after weighing and assessment	34
Table 3.2 Three drying schedule for DST of seven-year-old <i>Acacia mangium</i>	41
Table 3.3 Three drying schedule for DST of 10-year-old <i>Acacia mangium</i>	42
Table 4.1 Moisture content and shrinkage of seven and 10-year-old <i>Acacia mangium</i>	45
Table 4.2 Comparison of wood physical properties of seven and 10-year-old <i>Acacia mangium</i>	46
Table 4.3 Drying defects level and critical drying condition for seven-year-old <i>Acacia mangium</i>	59
Table 4.4 Drying defects level and critical drying condition for 10-year-old <i>Acacia mangium</i>	60
Table 4.5 Results on DST 1, DST 2 and DST 3 of seven-year-old <i>Acacia mangium</i>	63
Table 4.6 Result on DST 1, DST 2 and DST 3 of 10-year-old <i>Acacia mangium</i>	66
Table 4.7 Recommended drying schedule for seven-year-old <i>Acacia mangium</i>	67
Table 4.8 Recommended drying schedule for 10-year-old <i>Acacia mangium</i>	68

LIST OF FIGURES

	Page
Figure 2.1 Illustration of wet pocket	14
Figure 3.1 Bucking of felled <i>Acacia mangium</i> tree	24
Figure 3.2 Through to through sawing pattern	25
Figure 3.3 Standard size of sample boards for pre-treatment	27
Figure 3.4 Strip (1) and strip (2) for initial moisture content determination	28
Figure 3.5 Incision pre-treatment	28
Figure 3.6 Pressure pre-treatment of <i>Acacia mangium</i>	30
Figure 3.7 Hilderbrand experimental kiln drying machine facility	31
Figure 3.8 Control panel (DBT and WBD control button	31
Figure 3.9 Slot in pockets for sample boards arrangement in Hilderbrand Experimental Dryer	32
Figure 3.10 Strip for determine final moisture content and wet pocket	32
Figure 3.11 Sample boards for Quick Drying Test (QDT)	33
Figure 3.12 Surface and end checks in Quick Drying Test (QDT) sample boards	35
Figure 3.13 Deformation in dried <i>Acacia mangium</i>	36
Figure 3.14 Honeycombing in dried <i>Acacia mangium</i>	36
Figure 3.15 Collapse and honeycombing in dried <i>Acacia mangium</i>	37
Figure 3.16 Wet pocket in dried <i>Acacia mangium</i> boards	37
Figure 3.17 Sequence and pathway in developing a new drying schedule	39
Figure 3.18 Semi-logarithms scale-graph of seven-year-old <i>Acacia mangium</i>	39
Figure 3.19 Sample boards for Drying Schedule Test (DST)	40
Figure 3.20 Flowchart of methodology	44
Figure 4.1 Drying time of seven-year-old <i>Acacia mangium</i> of quarter sawn sample 47 boards	47

Figure 4.2	Drying time of seven-year-old <i>Acacia mangium</i> of rift sawn sample boards	48
Figure 4.3	Comparison of drying rate of seven-year-old <i>Acacia mangium</i> between different sawing pattern boards	49
Figure 4.4	Drying time of 10-year-old <i>Acacia mangium</i> for quarter sawn sample boards	50
Figure 4.6	Comparison of drying rate of 10-year-old <i>Acacia mangium</i> between sawn boards	51
Figure 4.7	Wet pocket in <i>Acacia mangium</i> rift sawn boards	52
Figure 4.8	Wet pocket in <i>Acacia mangium</i> quarter sawn boards	52
Figure 4.9	Mean area of wet pocket developed in seven-year-old <i>Acacia mangium</i>	53
Figure 4.10	Average area of wet pocket developed in seven-year-old <i>Acacia mangium</i>	54
Figure 4.11	Drying defects in quarter sawn boards of seven-year-old <i>Acacia mangium</i>	57
Figure 4.12	Drying defects in rift sawn boards of seven-year-old <i>Acacia mangium</i>	57
Figure 4.13	Drying defects in quarter sawn boards of 10-year-old <i>Acacia mangium</i>	58
Figure 4.14	Drying defects in rift sawn boards of 10-year-old <i>Acacia mangium</i>	58
Figure 4.15	Drying Schedule Test 1 (DST 1) of seven-year-old <i>Acacia mangium</i>	61
Figure 4.16	Drying Schedule Test 2 (DST 2) of seven-year-old <i>Acacia mangium</i>	62
Figure 4.17	Drying Schedule Test 3 (DST 3) of seven-year-old <i>Acacia mangium</i>	62
Figure 4.18	Drying Schedule Test 1 (DST 1) for 10-year-old <i>Acacia mangium</i>	64
Figure 4.19	Drying Schedule Test 3 (DST 3) for 10-year-old <i>Acacia mangium</i>	65
Figure 4.20	Drying Schedule Test 2 (DST 2) for 10-year-old <i>Acacia mangium</i>	65

LIST OF ABBREVIATIONS

<i>A.mangium</i>	<i>Acacia mangium</i>
ANOVA	Analysis of Variance
ASTM	American Society for Testing and Materials
cm	Centimetre
DBT	Dry Bulb Temperature
DST	Drying Schedule Test
EMC	Equilibrium Moisture Content
FSP	Fibre Saturation Point
GMC	Green Moisture Content
RH	Relative Humidity
Hrs	Hours
MC	Moisture Content
MC _i	Initial Moisture Content
MC _f	Final Moisture Content
m	Meter
mm	Millimetre
QDT	Quick Drying Test
SG	Specific Gravity
WBD	Wet Bulb Depression
WBT	Wet Bulb Temperature

CHAPTER 1

INTRODUCTION

1.1 Study Background

Acacia mangium is a commercial plantation species planted widely in Southeast Asia. Its ability to tolerate and adapt to adverse climate and condition make it preferable to be planted on a large scale. At least 2.6 million hectares of *A. mangium* plantations were established in Southeast Asia (Nambiar & Harwood, 2014). As of June 2019, Sarawak has established 452,760.45 ha of forest plantations, of which 69% are planted with *A. mangium* (Forest Department Sarawak, 2019). The total production of logs from all planted forests in Sarawak in 2019 was 1,664,305 m³ (Forest Department Sarawak, 2019). In Sarawak, *A. mangium* is widely used for commercial reforestation programmes to reduce timber dependency from the natural forest and sustain natural forests.

Initially, *A. mangium* was planted for pulp and paper due to its trait in producing a good quality pulp and high pulping ability. However, over time, new breeds of *A. mangium* will be available and might have superior characteristics in term of wood quality, which can be utilized as the primary timber source for the local wood-based industry especially furniture. The delicate appearance, grain orientation, and colour of the wood itself increased the wood aesthetic value and suitable for converting a high-value products at a premium price. The wood has acceptable strength, quality and durability if it utilized properly and managed appropriately.

Wood drying is the most crucial process in timber manufacturing. Timber can be drying by using air drying, but it is time-consuming. Kiln drying used to dry timber in this

modern era to accelerate drying. However, kiln drying must be adequately monitored especially the setting of the kiln dry itself. Extreme drying setting and rapid drying time can reduce the end quality of the wood by developing drying defects such as cracking, checking and case hardening (Kettula, 2015).

Acacia mangium is known as a hard to dry plantation tree species due to its refractory properties. Zafhian et al. (2020) stated that the conventional method for drying *A. mangium* is very demanding to achieve a consistent result in drying *A. mangium* wood. Drying is the detrimental stage of wood processing for *A. mangium*. Error in wood drying of *A. mangium* will influence the dimensional stability, finishing process, glueing ability and workability (Tenorio & Moya, 2011). Dimension instability in *A. mangium* wood occurred due to the variations in the distribution of moisture content (MC) in a single board attributed to the presence of the wet pocket. Wet pockets likely to occur in the quarter and rift sawing grain pattern of the wood and double rift sawing grains pattern of the wood (Tenorio & Moya 2011; Gan et al., 2015).

A wet pocket is defined as a particular area in heartwood with adversely huge MC (Watanabe et al., 2010). The presence of wet pockets can be detected after drying by observing the area with dark brown colour. The area with wet pockets normally has a darker colour than the normal area of the wood without wet pockets. The moisture content of wet pockets in *A. mangium* ranged from 12 to 76% and average at 25% (Tenorio et al., 2012). It is also likely that these areas will collapse, split and check during drying.

It was suggested that wet pockets in heartwood are related to the presence of bacteria (Lihra et al., 2000). Vessels also can be clogged and blocked by bacteria and tyloses,

respectively and restricting the flow of water in the wood (Sun et al., 2006). Wet pockets in *Gmelina arborea* was attributed to anaerobic type bacteria (Moya & Muñoz, 2008).

There are some techniques or methods reportedly able to reduce wet pockets and final moisture content (MC_f). For instance, hot water bath and microwave pre-treatments of *A. mangium* boards can relieve the occurrence of wet pockets (Gan et al., 2015). However, this method might not be feasible in a commercial setting due to establishing large water bath and microwave facilities. Pre-drying using airflow velocity 100 rpm in room temperature condition (21 °C and RH 52%) before kiln drying of alpine fir, hemlock and western red cedar partially reduce moisture content differences between wet pockets and normal wood (Warren et al., 1995).

Moya et al. (2009) reported that wood with wet pocket have low permeability. Thus, it will slow down the drying and contribute to uneven MC_f. Air pressure pre-treatment, known as micro explosion pre-treatment, is a new technology that was introduced to treat and improve the permeability of the Poplar wood. Before this, steam pre-treatment is reported effective in improving the permeability of the wood and reduced the drying period but steam pre-treatment is cost and times consuming as it requires a long cycle of the process (Ma et al., 2015). Both of these pre-treatments are similar to each other and able to weaken and break down the bordered pit pairs in the wood to reach the wet pockets area and improve the permeability of the wood (Ma et al., 2015).

Another pre-treatment method introduced by Zhao et al. (2015) is by modifying the wood treatment and preservation method known as the wood compression method. This wood compression method was used to force out the air inside the wood. During wood drying, this compression method can help in improving the permeability of the wood. Two

types of wood compression methods introduced are tangential and radial compression described in Zhao et al. (2015). Through wood compression, the thin-walled tyloses can be broken down thus the permeability of the wood by rupturing the pit in the wood the improves the flow of the water through the wood layer (He et al., 2017).

Sorting of lumber before kiln drying can alleviate wet pockets and reduce the chance of over-drying of lumber. Apart from that, sorting of lumber can avert the under or over-drying and low timber quality. Separating *Vochysia guatemalensis* boards according to the distance from the pith, vertical parts of tree, heartwood and sapwood reduced moisture content variability, which produced improved dried timber quality (Moya et al., 2011).

Tenorio and Moya (2011) have modified their first drying schedule to reduce the moisture content of the *A. mangium* wood. Their study showed there was still a lack of uniformity of the moisture content due to the presence of the wet pockets. A mild drying schedule is recommended to consider the refractory nature of *A. mangium* wood and its tendency to show honeycomb in kiln-dried boards (Tan, 2014).

Thus, it is crucial to determine the right temperature and drying condition for *A. mangium* wood by manipulating the current drying schedule to avoid irregular and excessive wood shrinkage. Apart from minimizing the occurrence of the wet pockets within and between the sections of the board after drying, the data will be helpful for both utilization of the *A. mangium* in Sarawak and the determination of the suitable condition in obtaining lumber with lower and uniform MC. All the drying process need to be well under control to prevent any drying defects, uneven moisture distribution and wet pocket in *A. mangium*.

1.2 Problem Statement

Acacia mangium accounts for 67% of the forest plantation area planted in Sarawak, with the estimated current productivity of about 180 m³/ha for a 12-year cycle. It was anticipated at least 3 million m³ of the log would be produced annually in the coming year. Initially, the resource from the early planting of the *A. mangium* was only targeted for the fibre industry. However, if the sawn timber thickness of the *A. mangium* more than 31 mm (1 1/4 inch) can be obtained from the lower portion of the *A. mangium*, these logs may produce value-added products, such as furniture. However, it must be economically dried before processing.

The current empirical practice of drying *A. mangium* is air drying for about a month before kiln drying at conventional temperature for another month. This practice aimed to ensure the *A. mangium* boards dried evenly and dimensionally stable during the service. However, this practice cannot be pertained especially for small timber industry due to limited space available in the mills for air drying. Besides, air drying was time-consuming and not economical for the industry. Drying too fast, the *A. mangium* boards were hampered with collapse, causing irregular; excessive shrinkage and consequently forming wet pocket within the sections of the board. The boards have irregular surface and thickness but are dimensionally unstable due to a considerable variation in moisture content. Sawn timber boards with these characteristics would be unsuitable for indoor joinery as well as the furniture industry. Thus, it is important to find ways to accelerate the drying of *A. mangium* boards so that they can be utilized as raw material for many other products apart from the fibre industry.

1.3 Objectives

The main aims of this study were to assess the effect of pre-treatment of *A. mangium* wood on the moisture content after drying and develop a drying schedule. The specific objectives were to: -

- i. determine the untreated moisture content and physical properties of seven and 10-year-old *A. mangium*.
- ii. determine the effects of pre-treatments on the drying rate, occurrence of the wet pocket and drying defects in dried pre-treated *A. mangium* boards; and
- iii. develop a new drying schedule for seven and 10-year-old *A. mangium* based on Quick Drying Test (QDT).

1.4 Chapter Summary

Due to the uneven distribution of wet pockets and large variation of MC value in single boards of *A. mangium*, the utilization of *A. mangium* was limited to chips and fibre products. Its inherent and refractory properties make it difficult to be converted to furniture, joinery and construction materials. Quarter and rift sawing grains patterns of *A. mangium*, especially at the lower part of the logs, have a high incidence of wet pockets. The lower part of *A. mangium* log consists of high percentages of heartwood and have low permeability. It has the potential to be converted to high-end value products if the incident of wet pockets and uneven distribution of MC can be reduced and eliminated. Thus, a proper drying schedule and process must be implemented. The main aims of this study were to assess the effect of pre-treatment of *A. mangium* wood on the moisture content and the physical

properties of seven and 10-years-old *A. mangium*; effects of pre-treatments on drying of *A. mangium* and develop a drying schedule for both seven and 10-year-old *A. mangium*.